TOKORO LAB.

[Resource Circulation, Separation-Concentration, Powder Processing]


Endowed Research Unit for Non-ferrous Metal Resource Recovery Engineering (JX Metals Endowed Unit)

Environmental Resource Processing Engineering

http://www.metals-recycling.iis.u-tokyo.ac.jp/chiharutokoro.html http://www.tokoro.env.waseda.ac.jp/

Technologies for Resource Circulation / Environmental Restoration

Valorization of the urban mine resources and refractory ores by advanced technologies for solid separation and concentration.



Smelting High-purity Refining

Secondary raw Materials material Refractory ores Separation Mining Concentration

Special Grinding Technologies for Separation of Solids

Soil Remediation by surface grinding





Mineral Liberation Analyzer (MLA)



Increase of SiO. exposure by removal of surface Concentration of

Mn into a fine particle fraction

Solid analysis to investigate the mineral separation Identification of

the mineral phases Quantification of liberation degree and weight ratio of each mineral

- Selective separation and peeling at interface by control of voltage, current, resistance and discharge path in electric nulsed charge
- Creating a new recycling loop

Control of minerals separation by microwave irradiation

High-selective separation by novel electric pulsed charge

- Selective liberation of mineral phases by heat a. crack formation at phase boundaries due to different thermal expansion
- b. selective change of surface properties

Optimization of grinding operations by simulations

Recovery of magnetite by slow-cooling crystallization Study of the separation of magnetite from an amorphous phase slag via

Analysis of substrate and fluid behavior in the crusher

- > Estimation of grinding performances by analysis of collisions between stirrer and substrate
- Possible elucidation of stirring and granulation mechanisms

Pretreatment Operations for Improving the Solid Separation

composition particle by

Recovery of Co from Li-Ion batteries by slow heating

spectra of particles

batteries (LIB)







smooth-cooling crystallization and magnetic separation --- I'C/min



Magnetite particle size and precipitation rate increased by decreasing the cooling rate

Advanced Technologies for Environment Remediation


As removal by surface precipitation



Study and optimization of surface precipitation Removal and recovery of inorganic elements in high

efficiency

Removal enhancement by amorphization



Calcination of MgCO₃ to MgO and quenching to suppress crystallization

Process optimization by combination of geochemical modeling and fluid analysis



- Creation of ground model from terrain data and reproduction of the dynamic shape water bodies
- Prediction of concentration profiles by considering chemical equilibria

